TECHNICAL BULLETIN

UPC Spray-Applied Polyurethane Foam Material Compatibility & Chemical Resistance

UPC SPF is compatible with many different building materials, including but not limited to:

| | · | | |
|----------------------------|----------------------------|-------------------------------------|--|
| Gypsum Board | Exterior Gypsum Board | Steel Studs | |
| CMU | Concrete | Polyethylene/PEX Tubing | |
| Polypropylene | PVC/CPVC | Polyisocyanurate Board | |
| Aluminum | Copper | Common Electrical Wiring | |
| OSB | Vinyl | Stainless Steel | |
| ABS | Carbon Steel | Galvanized Metal | |
| Plywood | Wood Studs | One Component Polyurethane Foams | |
| Common Batt Insulations | Common Blow-In Insulations | Common Low Voltage Wiring | |

UPC SPF is chemically resistant to many common substances, including but not limited to:

| Non-Distilled Petroleum Products | Limited Moisture (Water) Resistance | Nonionic soaps |
|-------------------------------------|--|----------------|
| Gypsum mud | Tar | Acrylics |
| Silicones | Polyurethanes | Polyureas |
| Petroleum Combustion Exhaust | Caulks | Cement |

It is the foam applicator's responsibility to ensure the system is being applied within physical parameters. Proper applications may require adjustments to one or more of the following: spray techniques, substrate, application, or job site temperature.

All surfaces to be sprayed with foam should be clean, dry and free of dew or frost. Metal substrate must be free of any surface residue such as oil, grease, etc.



TECHNICAL BULLETIN

Recommended application procedure when applying UPC spray polyurethane foam over **Chlorinated Polyvinylchloride (CPVC)**:

| | PASŞ | |
|-----------------|----------|----------|
| PRODUCT | 1st | 2nd+ |
| UPC Open Cell | 3 inches | 6 inches |
| UPC Closed Cell | 0.5 inch | 2 inches |

Disclaimer. It is the responsibility of the applicator to ensure equipment and ambient/substrate conditions are appropriate for SPF application. It is the responsibility of the applicator and/or construction manager ultimately to prove product suitability. Sufficient time must be allowed for SPF to cool between passes. For more information, please refer to product technical data.

Recommended application procedure when applying UPC spray polyurethane foam over **PEX Tubing**:

| | PASS | | |
|-----------------|------------|----------|----------|
| PRODUCT | 1st | 2nd | 3rd+ |
| UPC Open Cell | 3.5 inches | 6 inches | 6 inches |
| UPC Closed Cell | 0.5 inch | 1 inch | 2 inches |

Disclaimer: It is the responsibility of the applicator to ensure equipment and ambient/substrate conditions are appropriate for SPF application. It is the responsibility of the applicator and/or construction manager ultimately to prove product suitability. Sufficient time must be allowed for SPF to cool between passes. For more information, please refer to product technical data.

Recommended application procedure when applying UPC spray polyurethane foam over **Common Electrical Wiring**:

| | PASŞ | |
|-----------------|----------|----------|
| PRODUCT | 1st | 2nd+ |
| UPC Open Cell | 3 inches | 6 inches |
| UPC Closed Cell | 0.5 inch | 2 inches |

Disclaimer: It is the responsibility of the applicator to ensure equipment and ambient/substrate conditions are appropriate for SPF application. It is the responsibility of the applicator and/or construction manager ultimately to prove product suitability. Sufficient time must be allowed for SPF to cool between passes. For more information, please refer to product technical data.